

U. S. DEPARTMENT OF AGRICULTURE  
 AGRICULTURAL MARKETING SERVICE, COTTON PROGRAM  
 ABILENE, TX 79606 TELEPHONE: 325-690-9378  
 KENNY DAY, AREA DIRECTOR

QUALITY OF SAMPLES	401,754		FRIDAY , 12/04/15			
	WEST TEXAS		OKLAHOMA		KANSAS	
	WEEK	SEASON	WEEK	SEASON	WEEK	SEASON
	41,638	262,117	21,260	131,073	1,270	8,564
<b>COLOR GRADES</b>						
11 & 21	13.3	27.4	20.1	53.8	0.0	0.0
31	38.7	23.0	46.3	24.4	0.0	0.0
41	13.8	6.8	8.9	3.8	0.0	0.0
51	0.2	0.1	0.1	0.0	0.0	0.0
61	-	-	-	-	0.0	0.0
71	-	-	-	-	0.0	0.0
12 & 22	5.5	16.8	6.5	7.5	0.0	0.0
32	18.6	16.4	12.9	6.9	0.0	0.0
42	7.5	4.8	2.2	0.8	0.0	0.0
52	0.1	0.0	0.1	0.0	0.0	0.0
62	-	-	-	-	0.0	0.0
13 & 23 & 33	1.4	3.8	2.1	2.3	0.0	0.0
43	0.8	0.4	0.7	0.2	0.0	0.0
53	0.0	0.0	0.0	0.0	0.0	0.0
63	-	-	-	-	0.0	0.0
24,34, 44, 54	0.1	0.4	0.1	0.4	0.0	0.0
BG'S	0.0	0.0	0.0	0.0	0.0	0.0
<b>LEAF GRADES:</b>						
1 & 2	20.0	38.8	16.9	48.5	0.0	0.0
3	41.6	35.1	44.5	33.1	0.0	0.0
4	24.0	17.4	26.7	13.4	0.0	0.0
5	10.5	6.3	9.6	4.0	0.0	0.0
6	3.2	1.8	2.2	0.9	0.0	0.0
7	0.6	0.5	0.2	0.1	0.0	0.0
BG'S	0.2	0.1	0.0	0.0	0.0	0.0
<b>AVERAGE LEAF:</b>	3.4	2.9	3.3	2.6	0.0	0.0
<b>BARK:</b>						
GRASS	12.3	10.4	8.4	5.8	0.0	0.0
CRACKED SEED	0.0	0.0	0.0	0.0	0.0	0.0
	-	0.1	-	-	0.0	0.0
<b>AVERAGE UNIFORMITY:</b>	80.6	80.3	81.8	81.5	0.0	0.0
<b>STAPLES (32nd)</b>						
30 & SHORTER	0.0	0.0	-	0.0	0.0	0.0
31	0.5	0.5	0.0	0.1	0.0	0.0
32	2.0	4.0	1.2	1.1	0.0	0.0
33	10.2	15.1	2.1	4.1	0.0	0.0
34	18.9	22.7	7.2	8.1	0.0	0.0
35	19.9	19.9	13.6	12.8	0.0	0.0
36	19.5	17.6	25.6	25.0	0.0	0.0
37 & LONGER	29.0	20.2	50.4	48.8	0.0	0.0
<b>AVERAGE STAPLE:</b>	35.4	35.0	36.3	36.2	0.0	0.0
<b>MICRONAIRE</b>						
2.9 & LOWER	.1	.1	.2	0	0.0000	0.0000
3.0 - 3.2	0.8	0.8	1.4	0.9	0.0000	0.0000
3.3 - 3.4	1.7	1.5	2.2	2.7	0.0000	0.0000
3.5 - 4.9	93.6	93.3	95.2	95.5	0.0000	0.0000
5.0 & HIGHER	3.8	4.4	1	.9	0.0000	0.0000
<b>AVERAGE MICRONAIRE:</b>	4.3	4.3	4.2	4.1	0.0	0.0
<b>STRENGTH</b>						
21 & LOWER	-	-	-	-	0.0	0.0
22 - 23	0.0	0.1	-	-	0.0	0.0
24 - 25	0.6	0.7	-	0.0	0.0	0.0
26 - 27	3.8	3.8	0.2	0.5	0.0	0.0
28 - 29	25.5	27.0	6.1	6.8	0.0	0.0
30 & HIGHER	70.1	68.5	93.7	92.7	0.0	0.0
<b>AVERAGE STRENGTH:</b>	30.5	30.4	31.7	31.5	0.0	0.0