

U. S. DEPARTMENT OF AGRICULTURE  
 AGRICULTURAL MARKETING SERVICE, COTTON PROGRAM  
 ABILENE, TX 79606 TELEPHONE: 325/690-9378  
 KENNETH DAY, AREA DIRECTOR

QUALITY OF SAMPLES	1,670,504		05/05/17			
FINAL REPORT	WEST TEXAS		OKLAHOMA		KANSAS	
	WEEK	SEASON	WEEK	SEASON	WEEK	SEASON
	0	1,022,296	791	576,052	0	72,156
<b>COLOR GRADES</b>						
11 & 21	0.0	13.5	0.0	26.2	0.0	22.5
31	0.0	37.4	0.0	39.9	0.0	53.7
41	0.0	34.0	0.0	24.0	0.0	19.6
51	0.0	1.9	0.0	0.6	0.0	0.5
61	0.0	0.0	0.0	0.0	0.0	0.0
71	0.0	0.0	0.0	-	0.0	-
12 & 22	0.0	1.2	0.0	1.6	0.0	0.5
32	0.0	5.1	0.0	3.1	0.0	1.9
42	0.0	4.6	0.0	2.2	0.0	0.6
52	0.0	0.5	0.0	0.1	0.0	0.1
62	0.0	0.0	0.0	0.0	0.0	0.0
13 & 23 & 33	0.0	0.9	0.0	1.3	0.0	0.5
43	0.0	0.7	0.0	0.6	0.0	0.2
53	0.0	0.1	0.0	0.1	0.0	0.0
63	0.0	0.0	0.0	0.0	0.0	-
24,34, 44, 54	0.0	0.1	0.0	0.3	0.0	0.1
BG'S	0.0	0.0	0.0	0.0	0.0	0.0
	0.0	0.0	0.0	0.0	0.0	0.0
<b>LEAF GRADES:</b>						
1 & 2	0.0	30.8	0.0	33.9	0.0	12.2
3	0.0	43.0	0.0	44.7	0.0	41.1
4	0.0	19.3	0.0	15.6	0.0	29.1
5	0.0	5.4	0.0	4.5	0.0	12.6
6	0.0	1.2	0.0	1.0	0.0	3.8
7	0.0	0.3	0.0	0.2	0.0	0.9
BG'S	0.0	0.1	0.0	0.1	0.0	0.4
<b>AVERAGE LEAF:</b>	0.0	3.0	0.0	2.9	0.0	3.6
<b>BARK:</b>						
	0.0	19.8	0.0	9.3	0.0	23.6
<b>GRASS &amp; OTHER</b>	0.0	0.0	0.0	0.0	0.0	0.0
<b>AVERAGE UNIFORMITY:</b>	0.0	80.3	0.0	81.2	0.0	80.2
<b>STAPLES (32nd)</b>						
30 & SHORTER	0.0	0.0	0.0	0.0	0.0	-
31	0.0	0.0	0.0	0.0	0.0	-
32	0.0	0.4	0.0	0.1	0.0	0.0
33	0.0	2.1	0.0	0.9	0.0	0.1
34	0.0	8.0	0.0	5.2	0.0	3.0
35	0.0	20.5	0.0	17.2	0.0	22.6
36	0.0	30.8	0.0	31.0	0.0	38.4
37 & HIGHER	0.0	38.0	0.0	45.6	0.0	35.9
<b>AVERAGE STAPLE:</b>	0.0	36.1	0.0	36.3	0.0	36.1
<b>MICRONAIRE</b>						
2.9 & LOWER	0.0	0.2	0.0	0.1	0.0	7.6
3.0 - 3.2	0.0	1.0	0.0	0.7	0.0	12.7
3.3 - 3.4	0.0	2.2	0.0	1.3	0.0	13.0
3.5 - 4.9	0.0	93.2	0.0	88.1	0.0	66.7
5.0 & HIGHER	0.0	3.4	0.0	9.8	0.0	0.1
<b>AVERAGE MICRONAIRE:</b>	0.0	4.3	0.0	4.4	0.0	3.7
<b>STRENGTH</b>						
21 & LOWER	0.0	-	0.0	-	0.0	-
22 - 23	0.0	-	0.0	-	0.0	0.2
24 - 25	0.0	0.1	0.0	0.0	0.0	2.8
26 - 27	0.0	5.3	0.0	2.6	0.0	21.9
28 - 29	0.0	34.9	0.0	28.5	0.0	54.1
30 & HIGHER	0.0	59.7	0.0	68.9	0.0	21.0
<b>AVERAGE STRENGTH:</b>	0.0	29.9	0.0	30.3	0.0	28.4